

SETIPOL - SINGLE COMPONENT, ALIPHATIC, WATERPROOFING ACRYLIC RESIN

Waterproofing and elastic coating based on polymer resins and pigments, forming a completely bonded sheet on the support without joints or overlaps.

CE

USES

For waterproofing and protection of:

- roofs, terraces, balconies, etc ...
- protection and coating of the polyurethane foam TECNOFOAM from the UV rays and others climatological agents

NOTE: call our technical department about the application to other supports or situations

recommended consumption	± 2 kg/m ² (0,92 mm thickness)
tack-free at 23 °C	±1 hour
tensile strength at 23°C	> 0,5 MPa
elongation at 23°C	>200 %
dilution	water
application method	by brush, roll or "airless" equipment



COLORS

Grey
Red



2/3

GENERAL FEATURES

- High elasticity of the product, more than 200%.
- Great grip and adaptability. By presenting themselves as a paste-fluid, it adapts to all surfaces with ease of application in corners and inaccessible areas. The perfect grip does not allow the flow of water below the waterproofing, located much better, breakage of the blade.
- Advantages to the continuous sheets.
- Allows the formation of a seamless continuous sheet across the surface, avoiding possible errors in the welds.
- Do not apply at temperatures below 5 °C, or in rainy weather. Nor are applied to surfaces above 45 °C.

APPLICATION TYPES

- It can be applied by brush, roller or airless spray.
- Support properly clean (dust, moss, grease, ...), it must be dry.
- Ensure there are no detached surface parts should be removed.
- On tile and concrete shall be based on applying the first layer of product diluted with 15% water to increase the penetration and adherence of the same.
- Apply the first coat, with a consumption of about 0.750 kg/m², impregnating a glass fiber reinforcement and let dry.
- Apply a second layer with an approximate consumption of 0,750~1 kg/m². Final consumption should be 2 kg/m² so necessary a third application.

YIELD

Product yield is $\pm 2 \text{ kg/m}^2$ with a thickness of 1.5 mm, applied in one or various coats, depending on the application method and conditions.

PACKAGING

Metal tins of 25 kg.

SHELF LIFE

12 months at temperatures between 5°C and 35°C, provided it is stored in a dry place.

HANDLING

These safety recommendations for handling, are necessary for the implementation process as well as in the and post, on exposure to the loading machinery.

- Respiratory Protection: When handling or spraying use an air-purifying respirator.
- Skin protection: Use rubber gloves, remove immediately after contamination. Wear clean body-covering. Wash thoroughly with soap and water after work and before eating, drinking or smoking.
- Eye / Face: Wear safety goggles to prevent splashing and exposure to particles in the air.
- Waste: Waste generation should be avoided or minimized. Incinerate under controlled conditions in accordance with local laws and national regulations.

Anyway, consult the material and safety data sheet of the product (MSDS)



PROPERTIES

PROPERTIES	VALUES
Aspect	Thixotropic and colored liquid
Density at 23°C ISO 1675	± 1,4 g/cm ³
Viscosity at 23°C ISO 2555	±30.000 cps
Solid contents	±64%
Elongation at 23°C ISO 527-3	>200%
Tensile strength at 23°C ISO 527-3	>0,5 MPa
Tack free time at 23°C	2~4 hours
Temperature resistance service	-20~90 °C
Application temperature	5~45 ℃

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are only intended for sale to industrial and commercial customers. Customer assumes full responsibility for quality control, testing and determination of suitability of products for its intended application or use.

We warrant that our products will meet our written liquid component specifications. We make no other warranty of any kind, either express or implied, by fact or law, including any warranty of merchantability or fitness for a particular purpose. Our total liability and customers' exclusive remedy for all proven claims is replacement of nonconforming product and in no event shall we be liable for any other damages. While descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/ use, Tecnopol Sistemas S.L recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use.

No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth, or that the products, designs, data or information may be sued without infringing the intellectual property rights of others. In no case shall the descriptions, information, data or designs provided be considered a part of Tecnopol Sistemas S.L terms and conditions of sale. Further the descriptions, designs, data, and information furnished by Tecnopol Sistemas S.L hereunder are given gratis and Tecnopol Sistemas S.L assumes no obligation or liability for the description, designs, data or information given or results obtained, all such being given and accepted at the reader's risk. All data furnished refers to standard production using manufacturing testing tolerances. The product user, and not Tecnopol Sistemas S.L, is responsible for determining the suitability of our products for the user's intended use.

Liability of Tecnopol Sistemas and its affiliates for all claims is limited to the purchase price of the material.

Products may be toxic and require special precautions in handling. User should obtain detailed information on toxicity, together with proper shipping, handling and storage procedures, and comply with all applicable safety and environmental standards.

No freedom from any patents or other industrial or intellectual property rights is granted or to be inferred.

